



## SHANDONG TIANMAI CHEMICAL INDUSTRY CO., LTD

Add: LINZI QILU CHEMICAL INDUSTRY PARK WEST SIDE

WEILIU ROAD SHANDONG CHINA

Tel: 86-533-7488896, Fax: 86-533-7488895

Web: <http://en.chinatianmai.com>

# TECHNICAL DATA SHEET

## PRODUCT NAME:

### EPOXY RESIN E-12

#### Typical Properties

Items	Specification
Appearance	Pale granules
Epoxide Equivalent(100g/eq)	830-890
Softening Point (°C)	93-95
Organic Chlorine (eq/100g)	≤0.0025
Inorganic Chlorine (eq/100g)	≤0.0007
Color(Colorimetric assay Iron-Cobalt)	≤4
Volatile Matter(%)	≤0.2

#### Packaging

White PE bags of 25kg.

1.75 ton per pallet .

#### Storage

The resin in its original unopened bags is stable for more than 1 year, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practise any patented invention without a license.